

Bestendigheidlijst

Watsonit asbestvrije pakkingplaat

Pagina 1 van 4

+ Recommended

O Recommendation depends on operating conditions

N Not recommended

MEDIUM :

	BA-50	BA-F	BA-GL	BA-202	BA-N	BA-U BA-X	BA-C	BA-S BA-203	BA-R	BA-CF	BA- Auto	BA-SM
Acetamide	+	+	+	+	+	+	+	+	+	+	+	+
Acetic acid 10%	+	+	+	+	+	+	+	+	+	+	+	+
Acetic acid 100%	+	+	+	+	0	+	+	+	+	+	+	+
Acetic ether	0	0	0	0	0	0	0	0	0	0	0	0
Acetone	0	0	0	0	0	0	+	0	0	0	+	0
Acetylene	+	+	+	+	+	+	+	+	+	0	+	+
Adipic acid	+	+	+	+	+	+	+	+	+	+	+	+
Air	+	+	+	+	+	+	+	+	+	+	+	+
Alum	+	+	+	+	+	+	+	+	+	+	+	+
Aluminium acetate	+	+	+	+	+	+	+	+	+	+	+	+
Aluminium chlorate	+	+	+	+	+	+	+	+	0	+	+	+
Aluminium chloride	+	+	0	+	+	+	+	+	+	+	+	+
Ammonia	0	+	0	0	+	+	+	+	0	+	0	+
Ammonium bicarbonate	+	+	0	+	+	+	+	+	0	+	+	+
Ammonium chloride	+	+	0	+	+	+	+	+	0	+	+	+
Ammonium hydroxide	+	+	0	+	+	+	+	+	0	+	+	+
Amyl acetate	0	0	0	0	0	0	0	0	0	0	0	0
Aniline	N	N	N	N	N	N	N	N	N	N	0	N
Asphalt	+	+	+	+	0	+	0	+	+	+	+	+
Barium chloride	+	+	+	+	+	+	+	+	+	+	+	+
Benzene	+	+	+	0	0	+	N	+	0	+	N	0
Benzoic acid	+	+	+	+	+	+	+	+	+	+	+	+
Boric acid	+	+	+	+	+	+	+	+	+	+	+	+
Borax	+	+	+	+	+	+	+	+	+	+	+	+
Butane	+	+	+	+	+	+	+	+	N	+	N	+
Butyl alcohol	+	+	+	+	+	+	0	+	+	+	0	+
Butyric acid	+	+	+	+	+	+	+	+	+	+	+	+
Calcium chloride	+	+	+	+	+	+	+	+	+	+	+	+
Calcium hydroxide	+	0	0	+	0	+	+	+	+	+	+	+
Carbon disulphide	N	N	N	N	N	N	N	N	N	0	N	N
Carbon dioxide	+	+	+	+	+	+	+	+	+	+	+	+
Chloroform	+	0	0	0	0	0	0	0	0	0	N	0
Chlorine, dry	0	+	N	0	+	+	+	+	N	+	0	+
Chlorine, wet	N	0	N	N	N	0	0	N	N	0	N	N
Chromic acid	N	0	N	N	N	0	0	0	N	0	N	N
Citric acid	+	+	+	+	+	+	+	+	+	+	+	+
Copper acetate	+	+	+	+	+	+	+	+	+	+	+	+
Creosote	N	N	N	N	0	N	N	N	N	N	0	0

Bestendigheidlijst

Watsonit asbestvrije pakkingplaat

Pagina 2 van 4

+ Recommended

0 Recommendation depends on operating conditions

N Not recommended

MEDIUM :

	BA-50	BA-F	BA-GL	BA-202	BA-N	BA-U BA-X	BA-C	BA-S BA-203	BA-R	BA-CF	BA- Auto	BA-SM
Cresol	N	0	0	N	0	0	0	0	N	0	N	N
Cyclohexanol	+	+	+	+	+	+	+	+	0	+	0	+
Cyclohexanone	N	0	0	N	N	0	0	N	N	0	0	0
Decaline	+	+	+	0	+	+	+	+	0	+	N	0
Dibenzyl ether	N	N	N	N	N	N	N	N	N	N	N	N
Dimethyl formamide	N	N	N	N	N	N	N	N	N	N	N	N
Dowtherm	0	0	0	0	0	0	0	0	N	0	N	0
Ethane	+	+	+	+	+	+	+	+	0	+	+	+
Ethyl acetate	0	0	0	0	0	0	0	0	N	0	0	0
Ethyl alcohol	+	+	+	+	+	+	+	+	+	+	+	+
Ethyl chloride	0	0	0	N	0	0	N	0	0	0	N	N
Ethylene	+	+	+	+	+	+	+	+	0	+	+	+
Ethylene glycol	0	+	+	+	0	+	+	0	+	+	+	+
Formic acid 10%	+	+	0	+	+	+	+	+	+	+	+	+
Formic acid 85%	0	+	0	+	0	+	+	0	N	+	+	+
Formaldehyde	+	+	+	+	+	+	+	+	+	+	+	+
Freon 12	+	+	+	0	+	+	+	+	0	+	N	0
Freon 22	0	0	0	N	+	0	+	0	N	0	N	N
Fuel oil	+	+	+	+	+	+	+	+	+	+	0	+
Gasoline	+	+	+	0	+	+	+	+	+	+	N	0
Glycerin	+	+	+	+	+	+	+	+	+	+	+	+
Heptane	+	+	+	0	0	+	+	+	0	+	N	0
Hidraulic oil (mineral)	+	+	+	0	+	+	+	+	+	+	N	0
Hydraulic oil (type phosphate ester)	0	0	0	0	0	0	0	0	0	0	0	0
Hydraulic (glycol based)	+	+	+	+	+	+	+	+	+	+	+	+
Hydrazine	+	+	+	+	0	+	+	+	0	+	+	+
Hydrochloric acid 20%	0	+	+	0	0	0	+	0	N	0	0	0
Hydrochloric acid 36%	N	N	N	0	N	N	+	N	N	N	N	0
Hydrofluoric acid 10%	N	N	N	N	N	N	0	N	N	N	N	N
Hydrofluoric acid 40%	N	N	N	N	N	N	N	N	N	N	N	N
Hydrogen	+	+	+	+	+	+	+	+	0	+	+	+
Isobutane	+	+	+	+	+	+	0	+	N	+	0	+
Isooctane	+	+	+	0	+	+	+	+	+	+	N	0
Isopropyl alcohol	+	+	+	+	+	+	+	+	+	+	+	+
Kerosene	+	+	+	+	+	+	+	+	0	+	+	+
Lead acetate	+	+	+	+	+	+	+	+	+	+	+	+
Lead arsenate	+	+	+	+	+	+	+	+	+	+	+	+
Magnesium sulphate	+	+	+	+	+	+	+	+	+	+	+	+

Bestendigheidlijst
Watsonit asbestvrije pakkingplaat
Pagina 3 van 4

+ Recommended

0 Recommendation depends on operating conditions

N Not recommended

MEDIUM :	BA-50	BA-F	BA-GL	BA-202	BA-N	BA-U BA-X	BA-C	BA-S BA-203	BA-R	BA-CF	BA- Auto	BA-SM
Mallic acid	+	+	+	+	+	+	+	+	+	+	+	+
Methane	+	+	+	+	+	+	+	+	0	+	+	+
Methanol	+	+	+	+	+	+	+	+	+	+	+	+
Methyl chloride	N	0	0	0	0	0	0	0	N	0	N	0
Methylene dichloride	N	N	N	N	N	N	0	N	N	N	N	N
Methyl ethyl ketone	0	0	0	0	0	0	0	0	N	0	N	0
Milk	+	+	+	+	+	+	+	+	+	+	+	+
Mineral oil (type ASTM1)	+	+	+	+	+	+	+	+	+	+	+	+
Naptha	+	+	+	0	+	+	0	+	+	+	N	0
Nitric acid 20%	N	0	+	0	N	0	+	N	N	0	N	0
Nitric acid 40%	N	+	+	N	N	0	+	N	N	N	N	N
Nitric Acid 96%	N	N	N	N	N	N	N	N	N	N	N	N
Nitrobenzene	N	N	N	N	N	N	N	N	N	N	N	N
Nitrogene	+	+	+	+	+	+	+	+	+	+	+	+
Octane	+	+	+	0	+	+	+	+	+	+	N	0
Oleic acid	+	+	+	+	0	+	+	+	+	+	0	+
Oleum	N	N	N	N	N	N	N	N	N	N	N	N
Oxcalic acid	0	0	0	0	0	0	+	0	0	0	N	0
Oxygen	+	+	+	+	+	+	+	+	N	+	+	+
Palmitic acid	+	+	+	+	+	+	+	+	0	+	0	+
Pentane	+	+	+	0	+	+	+	+	0	+	N	0
Perchloroethylene	0	0	0	0	0	0	0	0	0	0	N	0
Phenol	N	N	N	N	0	N	0	N	N	N	0	N
Phosphoric acid	+	+	+	+	0	+	+	+	0	+	+	+
Potassium acetate	+	+	+	+	+	+	+	+	+	+	+	+
Potassium bicarbonate	+	+	+	+	+	+	+	+	+	+	+	+
Potassium carbonate	+	+	+	+	+	+	+	+	0	+	+	+
Potassium chloride	+	+	+	+	+	+	+	+	+	+	+	+
Potassium dichromate	+	+	+	+	+	+	+	+	+	+	+	+
Potassium hydroxide	+	+	+	+	0	+	+	+	0	+	+	+
Potassium iodide	+	+	+	+	+	+	+	+	+	+	+	+
Potassium nitrate	+	+	+	+	+	+	+	+	+	+	+	+
Potassium permanganate	+	+	+	+	+	+	+	+	+	+	+	+
propane	+	+	+	0	+	+	+	+	0	+	0	0
Pyridine	N	N	N	N	N	N	N	N	N	N	0	N
salicylic acid	+	+	+	+	+	+	+	+	+	+	+	+
Silicone oil	+	+	+	+	+	+	+	+	0	+	+	+
Soap	+	+	+	+	+	+	+	+	+	+	+	+

Bestendigheidlijst

Watsonit asbestvrije pakkingplaat

Pagina 4 van 4

+ Recommended

0 Recommendation depends on operating conditions

N Not recommended

MEDIUM :	BA-50	BA-F	BA-GL	BA-202	BA-N	BA-U BA-X	BA-C	BA-S BA-203	BA-R	BA-CF	BA- Auto	BA-SM
Sodium aluminate	+	+	+	+	+	+	+	+	+	+	+	+
Sodium bicarbonate	+	+	+	+	+	+	+	+	0	+	+	+
Sodium bisulphite	+	+	+	+	+	+	+	+	+	+	+	+
sodium carbonate	+	+	+	+	+	+	+	+	+	+	+	+
Sodium chloride	+	+	+	+	+	+	+	+	+	+	+	+
Sodium cyanide	+	+	+	+	0	+	+	+	0	+	+	+
Sodium hydroxide	0	0	N	0	0	0	+	0	0	+	0	0
Sodium sulphate	+	+	+	+	+	+	+	+	+	+	+	+
Sodium sulphide	+	+	+	+	+	+	+	+	+	+	+	+
Starch	+	+	+	+	+	+	+	+	+	+	+	+
Steam	0	+	+	0	+	+	+	+	+	+	+	+
Stearic acid	+	+	+	+	+	+	+	+	0	+	0	+
Sugar	+	+	+	+	+	+	+	+	+	+	+	+
Sulphuric acid 20%	N	+	N	N	N	0	+	N	N	0	N	N
Sulphuric acid 96%	N	N	N	N	N	N	+	N	N	N	N	N
Tar	+	+	+	+	+	+	+	+	+	+	0	+
Tartaric acid	+	+	+	+	+	+	+	+	+	+	+	+
Toluene	+	+	+	+	+	+	+	+	+	+	N	+
Transformer oil	+	+	+	+	+	+	+	+	0	+	0	+
Trichlorethylene	+	0	+	0	0	0	0	0	0	+	N	0
Water	+	+	+	+	+	+	+	+	+	+	+	+
White spirit	+	+	+	0	0	+	+	+	+	+	N	0
Xylene	0	N	0	0	N	0	+	0	0	+	N	0